

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 215 479 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
19.06.2002 Bulletin 2002/25

(51) Int Cl.7: **G01N 21/03**

(21) Application number: **01129230.7**

(22) Date of filing: **11.12.2001**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Brenneman, Allen J.**
Goshen, Indiana 46526 (US)
• **Wogoman, Frank W.**
Granger, Indiana 46530 (US)

(30) Priority: **12.12.2000 US 254626**

(71) Applicant: **Bayer Corporation**
Pittsburgh, PA 15205-9741 (US)

(74) Representative: **Burkert, Frank et al**
Bayer AG,
Konzernbereich RP
Patente und Lizenzen
51368 Leverkusen (DE)


(54) **Method of making a capillary channel**

(57) An optical reagent format with a precise capillary channel is made by molding a format on a carrier of a precise predetermined thickness. The carrier includes an insert at least a portion of which is molded in the format. Once the format is made, the insert is detached from the carrier and removed from the format leaving a precisely dimensioned capillary channel with an inlet and vent. A reagent may be applied in the capillary channel and the format used to measure the analyte in a fluid

such as blood.

An electrochemical sensor with a capillary channel is formed by placing a sacrificial insert and electrodes on a sensor base and applying plastic material. After the plastic material is cured, the sacrificial is removed leaving a capillary channel in the sensor. The inserts may be removed by a tool including a clamp for clamping and holding each insert stationary and a sliding block to which the sensor is secured.

Fig. 1



EP 1 215 479 A2

Description**FIELD OF THE INVENTION**

[0001] The present invention relates to precision capillary channels for sensors and the method of making them.

BACKGROUND OF THE INVENTION

[0002] Sensors are used for sampling a fluid, mixing the fluid with a reagent, and making an analysis of the mixed sample. One form of sensor includes a capillary channel between two optical paths and a reagent in the channel. Another sensor is injection molded with a capillary channel between a base and lid. Electrodes and a reagent are located in the channel. A test fluid is drawn into the channel by capillary action and reacts with the reagent. In the first sensor, a light source is applied to one of the optical paths, and light from the light source is transmitted through the fluid in the channel and directed to a detector applied to the other optical path. In the second sensor an electric current acrosses the electrodes is measured.

[0003] A significant problem in the fabrication of optical reagent sensors is the production of a precision optical path length. This has been achieved by producing an optically clear part having a cavity of a certain depth. The cavity is covered by an optically clear lid. The precise depth of the cavity is difficult to produce repeatedly, but even if the depth can be repeatedly produced, it is very difficult to attach a lid and control the path length due to the tolerances of the method of attachment. In addition, if the attachment uses adhesives, variations in adhesives adds to the tolerances. Other types of attachment such as sonic welding each has their own variability.

[0004] The difficulty in repeatedly producing a cavity of a precise depth is critical when producing an optical reagent sensor that is to be used in the transmission mode. In the transmission mode the path length in the capillary gap is directly proportional to an analyte being tested. If an identical analyte is measured in two sensors that have different path lengths, the results reported will be different due to the path lengths. There is a need for a method of making optical reagent sensors with precise capillary channels that can be reproduced without variances or tolerances.

[0005] Similarly, the formation of a capillary channel in an injection molded sensor is difficult to produce. The usual way to fabricate sensors of this type is to precision screen print active areas within a capillary area formed by a shaped top lid. It is desirable to reduce the cost and assembly required by this construction. Moreover, it is difficult to provide electrodes in a small molded capillary channel of less than .005 inch in height and it is desirable to provide a sensor of this size with molded electrodes so that such a sensor could be used for electro-

chemical analysis.

SUMMARY OF THE INVENTION

[0006] The present invention is directed to an optical reagent sensor and an electrochemical sensor and to a method for making an optical reagent sensor and an electrochemical sensor. The optical reagent sensor includes a precision capillary channel with an inlet and a vent. To fabricate such a sensor, a carrier made of a material that is chemically etched, punched, die cut or otherwise formed to a predetermined configuration and with precision thickness is provided as an insert. An optical sensor is molded onto the carrier and once the molded material is cured, the insert is detached from the carrier and removed from the sensor leaving a precise capillary channel in the sensor. A reagent can be applied to the channel for a particular analyte to be tested. The sensor is used by drawing a test fluid into the capillary channel.

[0007] The electrochemical sensor of the present invention includes individual electrodes or contacts molded into the sensor. This process includes placing a first electrode in a base mold and placing a sacrificial insert in the mold above the first electrode. A second electrode is then placed in the base mold over the insert. A top mold is placed on the base mold and plastic material is injected into the top and base molds. After curing, the sensor is removed from the mold and the sacrificial insert is removed leaving a capillary channel with the two contact/electrodes in the channel.

[0008] Since the force required to remove the insert from the fabricated sensor could be quite high, it is desirable to use a tool that clamps the insert securely in place while applying a force on the sensor. The tool includes a clamp for clamping the insert in a stationary position and a moveable block to which the sensor is secured. A drive mechanism is coupled to the block to move the block relative to the clamp thereby withdrawing the insert from the sensor.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] Other objects and advantages of the invention will become apparent upon reading the following detailed description and upon reference to the drawings in which:

FIG. 1 is a perspective view of a sensor format on a carrier;

FIG. 2 is a perspective view of a chain of sensor formats on a carrier;

FIG. 3 is an enlarged view of a sensor format removed from a carrier with a portion of the carrier between the legs of the format;

FIG. 4 is a reduced view of the sensor format illustrated in FIG. 3 with the portion of the carrier removed from between the legs of the format;

FIG. 5 is a perspective view of an alternative embodiment of the sensor format illustrated in FIGS. 1-4 on a carrier;

FIG. 6 is an enlarged view of the format illustrated in FIG. 5 with the carrier removed;

FIG. 7 is a perspective view of a bottom mold of a molding tool for molding an electrochemical biosensor with a first contact positioned in the bottom mold;

FIG. 8 is a view similar to FIG. 7 with a sacrificial protective insert positioned in the bottom mold;

FIG. 9 is a view similar to FIG. 8 with a second contact positioned in the bottom mold;

FIG. 10 is a perspective view of the molding tool with a top mold placed on the bottom mold;

FIG. 11 is an enlarged perspective view of a molded electrochemical biosensor with a sacrificial insert in the biosensor;

FIG. 12 is a perspective view of a tool used to remove the inserts from the biosensors illustrated in FIGS. 1-11;

FIG. 13 is a perspective view of an optical sensor with an insert;

FIG. 14 is a view similar to FIG. 13 with the insert withdrawn; and

FIG. 15 is a perspective view of the optical sensor of FIG. 13.

[0010] While the invention is susceptible to various modifications and alternative forms, specific embodiments thereof have been shown by way of examples in the drawings and will herein be described in detail. It should be understood, however, that it is not intended to limit the invention to the particular forms disclosed, but on the contrary, the intention is to cover all modifications, equivalents, and alternatives falling within the spirit and scope of the invention as defined by the appended claims.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0011] Referring to FIGS. 1-4, the sensor format 10 of the present invention is illustrated. The format 10 is an optical pipe formed of light transmission material. A light source is applied to an end 12 of a first leg 14 of the format 10. Light from the light source travels the length of the first leg 14 until it strikes a first end surface 16 that is at a 45° angle to the longitudinal axis of the first leg 14. The light is reflected by the end surface 16 through a capillary gap 18. Light that is not absorbed by material in the gap 18 strikes a second end surface 20 which is at a 45° to a longitudinal axis of a second leg 22 of the format 10. This light is reflected the length of the second leg 22 to a detector positioned at an end 24 of the second leg 22.

[0012] The format 10 is used in the transmission mode and the path length in the gap 18 is directly pro-

portional to an analyte being tested. If the same analyte is measured in two different formats that have different path lengths, the results reported will be different due to the different path lengths. The format 10 of the present invention is made in a manner to insure a capillary gap 18 of a precise thickness for each format 10 to minimize or eliminate any differences reported due to different path lengths through the gap 18.

[0013] The format 10 is formed by injection molding over a single carrier 26 with an insert 28 or a multiple carrier 30 with multiple inserts 32. The single carrier 26 and the multiple carrier 30 are of a material, such as metal, that can be chemically etched, laser cut, mechanically punched, die cut or a similar fabrication process, to a known precise thickness and configuration required to form a precise capillary gap 18. The thickness of the carriers 26 and 30 are dependent on the desired light path length of the gap 18. The carriers 26 and 30 can be formed of materials whose melt temperatures are above the melt temperature of the format material and the carrier material must have sufficient tensile strength to allow removal of the inserts 28 and 32 from the format 10 after the format 10 has been molded.

[0014] To mold a format 10, the single carrier 26 and the multiple carrier 30 are positioned and secured in a molding tool by tractor feed or pin position holes 34. Plastic material is injected into the molding tool and the formats 10 are formed on the single carrier 26 and the multiple carrier 30. Once the plastic material is cured and the carriers 26 and 30 removed from the molding tool, the inserts 28 and 32 are separated from the carriers 26 and 30, respectively, and removed from the formats 10 leaving a precise capillary gap 18. Each gap 18 is of the same size and thickness due to the precision thickness and dimension of the inserts 28 and 32. A reagent can be wicked into each gap 18 and dried. If the gap 18 must be sealed on the sides, lids (not shown) can be secured to the sides of the format 10 without being part of the optical path.

[0015] An extension 36 of each carrier 26 and 30 extends between the first leg 14 and the second leg 22 of each format 10 and provides an opaque light barrier between the legs 14 and 22 or light paths (FIG. 3). The extension 36 also provides structural integrity to the legs 14 and 22 and the format 10. If a light barrier or structural integrity is not needed, the extension 36 can be removed from between the legs 14 and 22 (FIG. 4).

[0016] A format 110 that requires sides to be sealed and provides a direct optical read is shown in FIGS. 5 and 6. The format 110 is injection molded onto a carrier 112 in a manner similar to the molding of the reagent format 10 in FIGS. 1-4. The carrier 112 is of the same material as the carriers 26 and 30 and fabricated in the same manner to a known precise thickness to form a precise capillary gap 114. The gap 114 is formed by an insert 116 that is part of the carrier 112.

[0017] The carrier 112 is positioned in a molding tool by tractor feed or pin position holes 118, and casting ma-

material is injected into the molding tool to form the formats 110. After the casting material has cured, the carrier 112 is removed from the molding tool and the inserts 116 are extracted from the formats 110 leaving the precise capillary gaps 114 of micron sizes. There is an entrance or inlet 117 to each gap 114 and a vent formed by extensions 119 on carrier 112 on a side opposite the inlet 118. The gap 114 is enclosed on the sides 114A and 114B and sides or a lid is not required to form the gap 114.

[0018] The format 110 includes a first cone 120 above the gap 114 and a second cone 122 below the gap. The shape of the cones 120 and 122 can be any shape such as square and need not be the truncated cone shape shown in the drawings. A light source is placed at an end 124 of the first cone 120 and a light or optical detector is placed at an end 126 of the second cone 122. Light from the light source travels through the first cone 120 to an analyte in the gap 114, and light passing through the gap 114 and the analyte passes along the second cone 122 to the optical detector for measurement of the analyte or other specimen. The cones 120 and 122 isolate the optical components (light source and detector) from the gap 114 and the specimen in the gap to prevent contamination. If contamination is not an issue, the cones 120 and 122 can be eliminated.

[0019] Referring to FIGS. 7-11 an electrochemical sensor 210 is illustrated. The sensor 210 includes a first electrode 212 and a second electrode 214 molded into the sensor 210 (FIG. 11). The sensor 210 also includes a precise small capillary channel formed by a sacrificial insert 216.

[0020] The sensor 210 is injection molded in a molding tool 218 having a bottom mold 220 and a top mold 222 (FIG. 10). The bottom mold 220 (FIGS. 7-9) includes a cavity 224 in the shape of the sensor 210. A plurality of locator pins 226, 228, 230, 232, 234, 236, 238 and 240 are provided on the bottom mold for properly locating the first and second electrodes 212 and 214 and the sacrificial insert 216.

[0021] The first and second electrodes 212 and 214 are loaded in the bottom mold 220 by stacking them such that the sacrificial insert 216 extends between them. The first electrode 212 is loaded first by fitting holes in the first electrode 212 over locator pins 226, 228 and 230 (FIG. 7). The sacrificial insert 216 is loaded next by fitting holes 238 and 240 in the insert over locator pins 238 and 240 (FIG. 8). The sacrificial insert 216 extends into the cavity 224 and over and on a forward end of the first electrode 212. The second electrode 214 is loaded in the bottom mold 220 onto locator pins 232, 234 and 236 with its forward end over and on the sacrificial insert 216 and over the forward end of the first electrode 212 (FIG. 9). The top mold 222 is then placed on the bottom mold 220 and compressed to provide compressive loading of both sides of the sacrificial insert 216. This compressive loading can be provided by raised portions in the bottom mold 220 and the top mold 222 that engage the sacrificial insert 216 between them

as the top mold 222 is mounted on the bottom mold 220.

[0022] Once the molding tool 218 is assembled (FIG. 10), plastic material is injected into the tool 218. Due to the compressive loading, the cavity 224 is filled with plastic material but since plastic can not flow into the stack of the forward ends of the first and second electrodes 212 and 214 and the insert 216, the plastic material does not flow between the forward ends of the electrodes 212 and 214 and the insert 216.

[0023] Once the plastic material has cured, the molding tool 218 is opened and the sensor 210 with the first electrode 212 and second electrode 214 and the insert 216 are removed. The insert 216 is then removed from the sensor 210 leaving a precise small capillary channel 242 (FIG. 11) with the first electrode 212 on the bottom of the channel 242 and the second electrode 214 on the top of the channel 242.

[0024] An optical version of the electrochemical sensor 210 is illustrated in FIGS. 13-15. In these FIGS. 13-15 there is illustrated an optical sensor 410. The optical sensor 410 is molded in a manner and tool similar to that for the sensor 210 except instead of electrodes 212, 214, the optical sensor 410 includes an access window 412 for source optics and an access window for detector optics directly below the access window 412. A capillary cavity or channel 414 is formed in the optical sensor 410 between the access windows so that light from source optics directed into the access window 412 passes through a specimen in the capillary cavity or channel 414 and is read by detector optics positioned at the lower access window.

[0025] A mold or tool that forms the optical sensor 410 includes inserts that are highly polished and extend into the mold. As plastic material is injected into the mold, the plastic material flows around the inserts to form the access windows. Since the inserts are highly polished, the access windows are clear with little distortion.

[0026] The capillary cavity or channel 414 is formed by an insert 416 that may be made of stainless steel or similar material. The insert 416 is similar to the insert 216 in FIGS. 7-11 and includes fitting holes 438 and 440 that fit over locator pins similar to pins 238 and 240 in a mold (FIG. 8).

[0027] Because the insert 416 is very thin and large pressures occur in the mold during molding of the optical sensor 410, an access hole 418 is formed in the optical sensor 410 by a portion of the mold that grips the insert 416 and holds it stable as plastic material flows around the insert 416. The optical sensor 410 also includes a hole 446 similar to the hole 346 in the sensor 210.

[0028] In each of the above described embodiments the insert 28 or 216 must be removed from the sensor 14 or 210, respectively, and the force required to do this could be quite high. Therefore, it is desirable to have a tool that will hold the sensor 14 or 210 securely in place and supply sufficient force inline to the insert 28 or 216 to withdraw the insert 28 or 216 from the sensor 14 or 210. An insert removal tool or extractor 300 to accom-

plish these objectives is illustrated in FIG. 12. The extractor 300 is secured to a base 312 and includes a clamp 314. The clamp 314 may be a DeStaca clamp with a handle 316 pivotally mounted on a stand 318. The stand 318 is secured to the base 312. The handle 316 is coupled to a clamp head 320 by a linkage 322 such that rotating the handle 316 causes the clamp head 320 to move toward and away from the base 312.

[0029] The base 312 includes a cavity 324 in which is positioned a sliding block 326. A cover plate 328 is secured to the base 312 over a portion of the cavity 324. The cover plate 328 has a slot 330 through which extends a drive pin and bearing 332 that are attached to the sliding block 326. An extraction drive lever 334 is pivotally mounted on the base 312 by a pin 336 and abuts the drive pin and bearing 332 such that as the extraction drive lever 334 is pivoted in a clockwise direction about the pin 336 as view in FIG. 12, the drive pin and bearing 332 are moved in the slot 330 moving the sliding block 326 out the end of the cavity 324.

[0030] To remove an insert 28, 216 or 416 the sensor 14, 210 or 410 (in FIG. 12 sensor 210 is illustrated) is placed in the cavity 324 with the holes 238 and 240 (FIG. 11) in the sensor 216 placed over the pins 342 and 344 which are rigidly mounted on the base 312. A hole 346 (FIG. 11) in the sensor 210 is positioned over a sensor pin 348 on the sliding block 326. Accordingly, the sensor 210 is secured to the sliding block 326 and the insert 216 is secured to the base 312. A force distribution block 340 is placed over the pins 342 and 344 and clamped down onto the insert 216 by the clamp 314.

[0031] The insert 216 is withdrawn from the sensor 210 by a force inline with the sensor 210 and insert 216 by pivoting the extraction drive lever 334 to move the sliding block 326 in the cavity 324. This action pulls the sensor 210 away from the insert 216 cleanly withdrawing the insert.

[0032] While the present invention has been described with reference to one or more particular embodiments, those skilled in the art will recognize that many changes may be made thereto without departing from the spirit and scope of the present invention. Each of these embodiments and obvious variations thereof is contemplated as falling within the spirit and scope of the claimed invention, which is set forth in the following claims.

Claims

1. A method of making an optical reagent format with a capillary gap, comprising:

providing a carrier with an insert, said carrier and insert being of a predetermined thickness;
placing said carrier in a mold;
molding a format onto said carrier and insert;
separating said insert from said carrier; and

removing said insert from said format leaving a capillary gap in said format.

2. The method of making an optical reagent format claimed in claim 1 further comprising applying reagent in said capillary gap.
3. The method of making an optical reagent format claimed in claim 1 said capillary gap having open sides, and sealing said open sides of said capillary gap.
4. The method of making an optical reagent format claimed in claim 1 further comprising removing said format from said carrier.
5. The method of making an optical reagent format claimed in claim 1 providing a plurality of carriers joined together and each including an insert, and molding a format onto each of said plurality of carriers and inserts.
6. The method of making an optical reagent format claimed in claim 1 said format including a pair of legs, further comprising forming said capillary gap between a pair of legs of said format.
7. The method of making an optical reagent format claimed in claim 1 wherein molding said format comprises molding a first format on an upper surface of said carrier and molding a second format on a lower surface of said carrier.
8. The method of making an optical reagent format claimed in claim 7 wherein said first and second formats are of a conical configuration.
9. A method of making an optical reagent format with a capillary gap, comprising:
 - providing a carrier of a predetermined thickness;
 - providing an insert on said carrier;
 - molding a format onto said carrier and said insert with a portion of said insert extending out of said format; and
 - removing said insert from said format to provide a capillary channel with an inlet and a vent in said format formed by said insert.
10. The method of making an optical reagent format claimed in claim 9 comprising removing said carrier from said format.
11. The method of making an optical reagent format claimed in claim 9 said insert comprising a material of a melt temperature higher than the melt temperature of the material of said format.

12. The method of making an optical reagent format claimed in claim 9 comprising molding said format with a first leg for the application of a light source and a second leg for the application of a light detector, said capillary channel being between said first and second legs. 5
13. The method of making an optical reagent format claimed in claim 9 comprising molding said format with a first conical member on a first side of said format and a second conical member on a second side of said format with said capillary channel between said first conical member and said second conical member. 10
14. A method of molding an electrochemical sensor using a sacrificial insert, comprising: 15
- providing a first mold;
inserting a first electrical contact in said first mold;
inserting a second electrical contact in said first mold;
closing said first mold with a second mold;
injecting material for forming a sensor into said closed first and second molds; 20
curing said material; and
extracting said sacrificial insert from said sensor. 25
15. The method of molding an electrochemical sensor claimed in claim 14 wherein extracting said sacrificial insert includes clamping said insert and moving said sensor relative to said insert. 30
16. An electrochemical sensor, comprising: 35
- a sensor base;
a sacrificial insert on said sensor base;
a first electrical contact and a second electrical contact in said sensor, said sacrificial insert positioned between said first electrical contact and said second electrical contact; and
plastic material on said sensor base and over said sacrificial insert, said plastic material of a formulation which allows removal of said sacrificial insert from said plastic material and said sensor base leaving a capillary channel in said casting material. 40
17. A tool for extracting a sacrificial insert from an electrochemical sensor, comprising: 45
- a clamp for clamping a sacrificial insert in a stationary position: 50
- a first block moveable relative to said clamp;
a drive member for moving said block relative to said clamp; and 55
- an attachment member on said block to attach a sensor with a sacrificial insert onto said block.
18. The tool claimed in claim 17 further comprising a base, said clamp including a second block secured to said base.
19. A sensor, comprising:
- a sensor body;
a first access window in said sensor body;
a second access window in said sensor body;
and
an insert in said sensor body between said first access window and said second access window.

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10





Fig. 11








Fig. 12







(11) **EP 1 215 479 A3**

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
08.10.2003 Bulletin 2003/41

(51) Int Cl.7: **G01N 21/03**, G01N 27/403,
B01L 3/00

(43) Date of publication A2:
19.06.2002 Bulletin 2002/25

(21) Application number: 01129230.7

(22) Date of filing: 11.12.2001

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
 MC NL PT SE TR**
 Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:

- Brenneman, Allen J.
Goshen, Indiana 46526 (US)
- Wogoman, Frank W.
Granger, Indiana 46530 (US)

(30) Priority: 12.12.2000 US 254626

(74) Representative: **Burkert, Frank et al**
Bayer AG,
Konzernbereich RP
Patente und Lizenzen
51368 Leverkusen (DE)

(71) Applicant: Bayer Corporation
Pittsburgh, PA 15205-9741 (US)


(54) Method of making a capillary channel

(57) An optical reagent format with a precise capillary channel is made by molding a format on a carrier of a precise predetermined thickness. The carrier includes an insert at least a portion of which is molded in the format. Once the format is made, the insert is detached from the carrier and removed from the format leaving a precisely dimensioned capillary channel with an inlet and vent. A reagent may be applied in the capillary channel and the format used to measure the analyte in a fluid

such as blood.

An electrochemical sensor with a capillary channel is formed by placing a sacrificial insert and electrodes on a sensor base and applying plastic material. After the plastic material is cured, the sacrificial is removed leaving a capillary channel in the sensor. The inserts may be removed by a tool including a clamp for clamping and holding each insert stationary and a sliding block to which the sensor is secured.

Fig. 1





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 12 9230

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	US 4 797 549 A (FATTIC GERALD T ET AL) 10 January 1989 (1989-01-10) * column 2, line 42 - line 59 * * column 3, line 5 - line 11 * * figure 5 *	1,9,10, 19	G01N21/03 G01N27/403 B01L3/00
Y	US 4 816 123 A (EVERAERTS FRANS M ET AL) 28 March 1989 (1989-03-28) * column 2, line 41 - line 56 * * claim 1; figure 2 *	1,9,10, 14,16,19	
Y	US 5 798 031 A (CHARLTON STEVEN C ET AL) 25 August 1998 (1998-08-25) * column 2, line 45 - line 62 * * figure 1 *	14,16	
A	EP 0 245 994 A (ICI AUSTRALIA LTD) 19 November 1987 (1987-11-19) * claims 1,8 *	1,2,9	
A	EP 0 287 883 A (MILES INC) 26 October 1988 (1988-10-26) * column 5, line 57 - column 7, line 5 * * column 8, line 22 - line 38 * * figure 1 *	1,2,9	TECHNICAL FIELDS SEARCHED (Int.Cl.7) G01N B01L
A	EP 0 210 071 A (ICL SCIENT) 28 January 1987 (1987-01-28) * claim 1 *	1,9	
A	US 5 437 999 A (DIEBOLD ERIC R ET AL) 1 August 1995 (1995-08-01) * column 8, line 15 - line 60 * * figure 5 *	14,16	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 20 August 2003	Examiner Krametz, E
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03/02 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 9230

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20-08-2003

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US 4797549	A	10-01-1989	NONE		
US 4816123	A	28-03-1989	DE	3783798 D1	11-03-1993
			DE	3783798 T2	19-05-1993
			EP	0241940 A2	21-10-1987
			JP	2735546 B2	02-04-1998
			JP	63006449 A	12-01-1988
US 5798031	A	25-08-1998	AU	724236 B2	14-09-2000
			AU	6482198 A	12-11-1998
			CA	2236132 A1	12-11-1998
			EP	0878708 A1	18-11-1998
			JP	10318971 A	04-12-1998
			NZ	329793 A	25-11-1998
			TW	400433 B	01-08-2000
EP 0245994	A	19-11-1987	EP	0245994 A2	19-11-1987
			JP	62273454 A	27-11-1987
EP 0287883	A	26-10-1988	AU	1452788 A	13-10-1988
			CA	1315181 C	30-03-1993
			EP	0287883 A1	26-10-1988
			JP	10000121 U	15-05-1998
			JP	63274839 A	11-11-1988
EP 0210071	A	28-01-1987	US	4637693 A	20-01-1987
			DE	3650701 D1	05-11-1998
			DE	3650701 T2	17-06-1999
			EP	0210071 A2	28-01-1987
			JP	1966036 C	25-08-1995
			JP	6097307 B	30-11-1994
			JP	62079409 A	11-04-1987
			US	RE33826 E	18-02-1992
US 5437999	A	01-08-1995	CA	2183865 A1	24-08-1995
			DE	69519725 D1	01-02-2001
			DE	69519725 T2	07-06-2001
			EP	0753051 A1	15-01-1997
			ES	2154330 T3	01-04-2001
			JP	3193721 B2	30-07-2001
			JP	9509740 T	30-09-1997
			WO	9522597 A1	24-08-1995

EPO FORM P0458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82